



REFERENCE INFORMATION*

COPPER TUBE

Size		Type K		Type L/ACR		Type M		DWV	
NOM	O.D.	HARD	COILS	HARD	COILS	HARD	COILS	HARD	
STANDARD LENGTHS		20' Lengths	60' thru 1-1/2 100' thru 1-1/4 40' and 60'-2" only	20' Lengths	60' thru 1-1/2 100' thru 1-1/4 40' - 2" only	20' Lengths	Consult	20' Lengths	
NOM	O.D.	WALL	WGT/FT	WALL	WGT/FT	WALL	WGT/FT	WALL	WGT/FT
1/4"	3/8"	.035	.145	.030	.126	.025	.106	—	—
3/8"	1/2"	.049	.269	.035	.198	.025	.145	—	—
1/2"	5/8"	.049	.344	.040	.285	.028	.204	—	—
5/8"	3/4"	.049	.418	.042	.362	.030	.263	—	—
3/4"	7/8"	.065	.641	.045	.455	.032	.328	—	—
1"	1-1/8"	.065	.839	.050	.655	.035	.465	—	—
1-1/4"	1-3/8"	.065	1.04	.055	.884	.042	.682	.040	.650
1-1/2"	1-5/8"	.072	1.36	.060	1.14	.049	.940	.042	.809
2"	2-1/8"	.083	2.06	.070	1.75	.058	1.46	.042	1.07
2-1/2"	2-5/8"	.095	2.93	.080	2.48	.065	2.03	—	—
3"	3-1/8"	.109	4.00	.090	3.33	.072	2.68	.045	1.69
3-1/2"	3-5/8"	.120	5.12	.100	4.29	.083	3.58	—	—
4"	4-1/8"	.134	6.51	.110	5.38	.095	4.66	.058	2.87
5"	5-1/8"	.160	9.67	.125	7.61	.109	6.66	.072	4.43
6"	6-1/8"	.192	13.90	.140	10.20	.122	8.92	.083	6.10
8"	8-1/8"	.271	25.90	.200	19.30	.170	16.46	—	—

FOR SPECIAL LENGTHS OR TEMPER CONSULT TUBE PRODUCTS DIVISION FOR PRICE AND AVAILABILITY

REFRIGERATION SERVICE TUBE

O.D. Size	1/8"	3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	7/8"	1-1/8"	1-3/8"	1-5/8"
WALL THICKNESS	.030	.030	.030	.032	.032	.032	.035	.035	.045	.050	.055	.060
WEIGHT PER FOOT	.0347	.0575	.0804	.109	.134	.182	.251	.305	.455	.655	.884	1.14
WEIGHT PER COIL+	1.74	2.88	4.02	5.45	6.70	9.10	12.55	15.25	22.75	32.75	44.20	57.00
COIL DIAMETER	14-3/4"	14-3/4"	14-3/4"	16-1/2"	16-1/2"	20"	22"	25"	27-1/2"	34-1/2"	39-1/2"	42"
COILS PER MASTER	10	10	10	10	10	5	5	3	3	—	—	—
WEIGHT PER MASTER	17.4	28.80	40.20	54.50	67.00	45.50	62.75	45.75	22.75	32.75	44.20	57.00

+STANDARD 50 FT. COIL – 100 FT COILS ALSO AVAILABLE AS STANDARD STOCK ITEM

TEMPERATURE CONTROL TUBE

PACKED 2000 FT PER WOOD BOX

O.D.	WALL	WGT/FT	O.D.	WALL	WGT/FT
1/4	.025	.0685	1/4	.032	.0849

PLASTIC COATED COPPER TUBE

Polyethylene coating made from low density LDPE resin and is extruded at 0.025" minimum wall.

*REFERENCE WALL THICKNESS, WEIGHTS , AND WGT/FT ARE NOMINAL.